


# ProRox® PS 960 ALU

with WR-Tech

ProRox PS 960 ALU is an aluminum foil faced mandrel wound pipe section. The insulation sections are made out of stone wool and are produced with an innovative water repellent binder called WR-Tech to mitigate the risk of corrosion under insulation.



## Application

The highly durable insulation sections are supplied split and hinged for easy snap-on assembly and are especially suitable for thermal and acoustic insulation of industrial pipe work.

## Product properties in accordance with EN 14303



Properties	Performance								Norms
Thermal conductivity at mean temperature	$T_m$ (°C)	50	100	150	200	250	300	350	EN ISO 8497
	$\lambda$ (W/mK)	0.040	0.046	0.054	0.064	0.077	0.092	0.112	
Maximum Service Temperature	650°C the outer surface temperature for ALU faced products should be limited to 80°C								EN 14707
Melting point	>1000°C								DIN 4102-17
Reaction to fire	Euroclass A <sub>2</sub> -S <sub>1</sub> ,d <sub>0</sub>								EN 13501-1
	Non Combustible Low flame spread characteristics								IMO 2010 FTPC
Nominal density (*)	≥ 100 kg/m <sup>3</sup>								EN 13470
Corrosion resistance	Trace quantity of water leachable chloride ions: ≤ 10 ppm								EN 13468
Water absorption	≤ 0.2 kg/m <sup>2</sup>								EN 13472
	≤ 0,2 kg/m <sup>2</sup> (After 24 hrs. pre-heating at 250°C)								
Water vapour diffusion resistance	$S_d > 200$ m								EN 14303
Air Flow Resistivity	> 80 kPa.s/m <sup>2</sup>								EN 29053
Influence on coating systems	Free from substances (e.g. silicone oil) that might impair surface wetting								VW 3.10.7
EN 14303 Designation code	MW EN 14303-T9(T8 if Do <150)-ST(+)-650-WS1-CL10-MV2								EN 14303
AGI Designation code	10.04.04.65.99								AGI Q132-06

(\*) ProRox insulation fully complies with EN 14303. Density is not an insulation property in itself, it only reflects the actual weight of the product per cubic meter.

## Compliance

- ProRox PS 960 ALU Pipe Sections fully comply with the requirements as set by internationally recognized standards like EN 14303, CINI 2.2.03, VDI 2055, ASTM C795, ASTM C547: Grade A for Type I, II, IV.
  - Above product properties reflect only to European (EN) standards. Compliance and Performance according to ASTM standards can be found on our website. Please contact our sales representatives for an extended list of approvals & certifications.
  - Validity of CE Marking & (AGI) designation code is restricted to the European production facilities.
- + Noise reduction data available in accordance to ISO 15665.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.